









FIELD TILE APPLICATION AREAS

	 INTERIOR FLOORS (DRY)	 INTERIOR WALLS	 PAVING	 EXTERIOR WALLS
FINISH				
RESIDENTIAL	NAT	NAT	–	NAT
LIGHT COMMERCIAL	NAT	NAT	–	NAT
HEAVY COMMERCIAL	NAT	NAT	–	NAT

RECOMMENDED USE













Weld is recommended for interior walls and floors, both in commercial and residential applications. The **NATURAL** finish can be used for residential and commercial floor and wall coverings. Weld is not recommended for exterior paving. If offset pattern is required for tiles 18" or longer, Mirage® recommends an offset of not greater than 30%. See www.mirageusa.net for further installations instructions .

SHADE and TEXTURE INDEX

 V1	 V2	 V3	 V4
UNIFORM APPEARANCE	SLIGHT VARIATION	MODERATE VARIATION	SUBSTANTIAL VARIATION
Minimal differences among tiles from the same production	Slight variation concerning texture and/or pattern	Colors or texture may vary significantly from tile to tile	Substantial variation in terms of colours and/or pattern from tile to tile

TILE PERFORMANCE DATA

CLASSIFICATION COMPLYING WITH ANSI A137.1

TECHNICAL CHARACTERISTICS	ASTM STANDARDS	ASTM TEST RESULT	ASTM TEST METHODS
 WATER ABSORPTION	< 0.50%	< 0.50%	C373
 FROST RESISTANCE	As Reported	Resistant	C1026
 BREAKING STRENGTHS	>250 lbf.	>400 lbf.	C648
 FACIAL DIMENSIONS RANGE	-3.0%<nominal<3.0%	Within Standard	C499
 RANGE OF THICKNESS (nominal)	<0.04 IN (1.02 mm max)	Within Standard	C499
 WEDGING	+/-0.50% OR +/- 2.0MM	Within Standard	C502
 WARPAGE	+/-0.75% OR +/- 2.3MM	Within Standard	C485
 CHEMICAL RESISTANCE	As Reported	Unaffected	C650
 STAIN RESISTANCE	As Reported	Unaffected	C1378
 SCRATCH HARDNESS	–	6	–
 DRY/WET COEFFICIENT OF FRICTION	As Reported	>0.60	C1028
 DYNAMIC COEFFICIENT OF FRICTION	D.C.O.F. > 0,42	>0.42	–

For specific certificates, please contact Mirage Usa (info@mirageusa.net) or your sales representative. Wet floorings can be slippery. It is recommended to consider and choose a specific collection and surface paying attention to the intended use.